

# Yorktown Flex-E-Clic II

Premium Vinyl Wood Plank



## PRODUCT QUICK SPEC

### 1. MANUFACTURER

Surface Source USA Inc.  
601 New Jersey Church Road  
Lexington NC 27292  
P (888)862-9898 F (678)626-0520  
[www.surface-source.us](http://www.surface-source.us)

### 2. PRODUCT DESCRIPTION

Yorktown Flex-E-Clic designed for use in commercial and residential applications. The Yorktown Flex-E-Clic collection features a natural wood look. Its rugged construction, including a 12 mil wear layer topped with Maxim Shield UV cured ceramic finish permits maximum durability ensuring long lasting beauty without the use of a floor finish. The composition ensures a 100% Pro-polymer **Virgin** PVC with fiberglass reinforced sheets. With excellent resistance to abrasion, chipping, cracking, and permanent indentations for heavy-duty performance requirements and to help conceal most substrate irregularities. Yorktown Flex-E-Clic is the perfect choice for basements, homes, office, banks, healthcare and condominiums, or wherever both function and high design are essential. The surface includes an micro bevel embossed surface to enhance the unique texture of wood, while adding slip resistance qualities to the plank. Precision cutting allows for easy Clic installation with tight seams.

**Available Styles (All Dimensions Nominal) Gauge:** 3/16" (4.2 mm)  
**Size:** 7.09" x 48" **Packaging:** 12 pieces per Carton (28.36 sq. /ft. per Carton)

### 3. TECHNICAL DATA

#### Product Classification

ASTM F 1700 - Solid Vinyl Tile; Class III, Type B

#### Fire Testing Information

ASTM E 648, Critical Radiant Flux - Class 1, > .45 W/cm<sup>2</sup>

#### General Performance Information

ASTM C1028-96, Static Coefficient of Friction .060 slip resistance  
Passes ADA/OSHA standard -

ASTM F 970, Static Load - 2,000 PSI, < .005"

ASTM F925, Resistance to Chemicals - No Change

ASTM F1514, Heat Stability of Color -  $\Delta E < 8$  Avg

ASTM F1515, Light Stability of Color -  $\Delta E < 8$  Avg

ASTM F1914, Residual Indentation - 3.4%

ASTM F2199, Dimensional Stability - .20" / in ft

ASTM E648 Critical Radiant Flux Class 1

ASTM F2753 Rolling load over Resilient .024 inch

### 4. TECHNICAL ASSISTANCE

Technical service information and assistance may be obtained  
1-888-662-9898 or [www.surface-source.us](http://www.surface-source.us)

### 5. LIMITED WARRANTY

**Limited One (1) Year Manufacturer's Warranty**

**Limited Twelve (12) Year Commercial Wear**

**Warranty Limited Twenty five (25) Year Residential  
Wear Warranty**



Bleached Pine LVP44165C



Boardwalk Oak LVP44152C



Coastal Oak LVP44153C



Old Towne Oak LVP44162C



Salem Oak LVP44161C



Rustic Walnut LVP44149C